



## ASM Aerospace Specification Metals Inc.

Contact Us

**AISI Type 410S Stainless Steel, tempered at test temperature plus 28°C, tested at 540°C (1000°F)**

**Subcategory:** Ferrous Metal; Heat Resisting; Metal; Stainless Steel; T 400 Series Stainless Steel

**Close Analogs:** AISI Type 410

**Key Words:** ASME SA240, ASTM A176, ASTM A240, ASTM A473, DIN 1.4001, JIS SUS 410 S, B.S. 403 S 17, martensitic

Component	Wt. %
C	Max 0.08
Cr	12.5
Fe	85
Mn	Max 1
P	Max 0.04
S	Max 0.03
Si	Max 1

### Material Notes:

16 mm diameter bar, heated to 980°C for 30 min., oil quenched, test temperature plus 28°C temper for 2 hours

Physical Properties	Metric	English	Comments
Density	<u>7.8 g/cc</u>	0.282 lb/in <sup>3</sup>	

### Mechanical Properties

Tensile Strength, Ultimate	<u>605 MPa</u>	87700 psi	
Tensile Strength, Yield	<u>565 MPa</u>	81900 psi	at 0.2% offset
Elongation at Break	<u>21.5 %</u>	21.5 %	in 50 mm

### Electrical Properties

Electrical Resistivity	<u>5.7e-005 ohm-cm</u>	5.7e-005 ohm-cm	at 20°C, 0.000108 Ohm-cm at 650°C
------------------------	------------------------	-----------------	-----------------------------------

Magnetic Permeability	700 - 1000	700 - 1000	annealed condition at RT
-----------------------	------------	------------	--------------------------

### Thermal Properties

CTE, linear 20°C	<u>9.9 μm/m-°C</u>	5.5 μin/in-°F	from 0-100°C (32-212°F)
CTE, linear 250°C	<u>11 μm/m-°C</u>	6.11 μin/in-°F	at 0-315°C (32-600°F)
CTE, linear 500°C	<u>11.5 μm/m-°C</u>	6.39 μin/in-°F	at 0-540°C, 11.7 μm/m-C at 0-650°C
Specific Heat Capacity	<u>0.46 J/g-°C</u>	0.11 BTU/lb-°F	from 0-100°C (32-212°F)
Thermal Conductivity	<u>24.9 W/m-K</u>	173 BTU-in/hr-ft <sup>2</sup> -°F	at 100°C; 28.7 W/m-K at 500°C
Melting Point	1480 - 1530 °C	2700 - 2790 °F	
Solidus	<u>1480 °C</u>	2700 °F	
Liquidus	<u>1530 °C</u>	2790 °F	
Maximum Service Temperature, Air	<u>705 °C</u>	1300 °F	Continuous Service
Maximum Service Temperature, Air	<u>815 °C</u>	1500 °F	Intermittent Service

### References for this datasheet.

Some of the values displayed above may have been converted from their original units and/or rounded in order to display the information in a consistent format. Users requiring more precise data for scientific or engineering calculations can click on the property value to see the original value as well as raw conversions to equivalent units. We advise that you only use the original value or one of its raw conversions in your calculations to minimize rounding error.